



SIMOLATM
VITRIFIED TILES

TECHNICAL SPECIFICATION

SIZE: 600X600X20 MM ,600X900X20 MM,800X800X20 MM

S. NO.	Test Conducted	Test Results	Remarks	
1	Water absorption (% by mass)	Average : 0.17	Based on the results of water absorption the tested tiles conformed to Gr. B lb (0.08% ≤ 3%) of IS 15622 : 2006, Further test results were delivered as per requirements of Gr. B lb	
2	Modulus Of Rupture (MOR) N/mm ² Span Length = 580 mm Average thickness of the tiles measured = 19.81 mm	Average : 39.0 N/MM ²	(Gr. B lb) Average 38 N/mm ² Individual 35 N/mm ² Minimum	Passed the test
S. NO.	Test Conducted	Test Results	Test Requirements As per IS 15622 : 2006	Remarks
3	Breaking Strength (N) Span Length = 580 mm Average thickness of the tiles measured = 19.81 mm	Average : 8090.0 N	(Gr. B lb) For thickness > 7.5 mm 1200 N minimum	Passed the test
4	Scratch Hardness Surface (Mohs' scale)	No. 7	(Gr. B lb) For commercial application 6 minimum, Home application 5 minimum	Passed the test
5	Thermal Shock Resistance	None of the tiles as tested showed any defects on surface at the end of the 10th cycle.	(Gr. B lb) Tiles specimens should not show any visible defect when subjected to thermal shock resistance test as per test method IS 13630 : 2006 (Part 5) with immersion	Passed the test
6	Bulk Density (gm/cc)	Average : 2.302	IS 13630 (Part 2) : 2006	
7	Co-efficient of Thermal Expansion from ambient Temperature to 100oC	L = 4.4956 (10 ⁶ K ¹) B = 4.6883 (10 ⁶ K ¹)	-----	Passed the test
8	Straightness of Sides (facial sides) The maximum deviation from straightness in percent related to the corresponding work sizes	+ 0.05 % (Max) - 0.08 % (Max)	(Gr. B lb) S > 410 cm ² ± 0.1 %	Passed the test
9	Rectangularity The maximum deviation from straightness in percent related to the corresponding work sizes	+ 0.10 % (Max) - 0.10 % (Max)	± 0.1 %	Passed the test
10	Surface Flatness The maximum deviation from flatness in percent (a) Centre of curvature related to diagonal calculated from work size. (b) Edge of curvature related to the corresponding work size (c) Warpage related to the diagonal calculated from the Work Size	+ 0.17 % (Max) + 0.10 % (Max) - 0.14 % (Max) + 0.09 % (Max) - 0.06 % (Max)	± 0.2 % ± 0.2 % ± 0.2 %	Passed the test Passed the test Passed the test

SIMOLA TILES LLP.

At. Nichi Mandal, Morvi-Halvad Road, Morbi - 363 642, Gujarat, India.

Ph. : +91 96389 33111, E-mail : info@simola.in, Web: www.simola.in

LLP Identification Number : - AAH-0031



SIMOLA™
VITRIFIED TILES

S. NO.	Test Conducted	Test Results	Test Requirements As per IS 15622 : 2006	Remarks
11	<p>Chemical resistance</p> <p>Five test specimens were treated with following solns.</p> <p>(a) Centre of curvature related to diagonal calculated from work size.</p> <p>(b) Edge of curvature related to the corresponding work size</p> <p>(c) Warpage related to the diagonal calculated from the Work Size</p> <p>Five test specimens were treated with following solns.</p> <p>1. Household Chemicals</p> <p>a) Ammonium Chloride soln. (100 gm/l)</p> <p>b) Standard cleaning Agent soln., (as per procedure)</p> <p>2. Swimming pool salts</p> <p>a) Sodium Hypochlorite Soln. (20 mg / l)</p> <p>b) Copper Sulphate Soln. (20 mg / l)</p> <p>3. Acids</p> <p>a) Hydrochloric acid Soln. 3 % (v/v)</p> <p>b) Citric acid Soln. (200 mg / l)</p> <p>4. Alkali</p> <p>Potassium hydroxide soln., (200 mg / l)</p>	<p>+ 0.17 % (Max)</p> <p>+ 0.10 % (Max) - 0.14 % (Max)</p> <p>+ 0.09 % (Max) - 0.06 % (Max)</p> <p>No visual changes observed after immersion for 6 hrs., pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 6 hrs., pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 6 hrs., pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 6 hrs., pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 7 days, pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 6 hrs., pencil lines removed with soft dry cloth.</p> <p>No visual changes observed after immersion for 7 days, pencil lines removed with soft dry cloth.</p>	<p>± 0.2 %</p> <p>± 0.2 %</p> <p>± 0.2 %</p> <p>" Class - AA " min.</p> <p>" Class - AA " min.</p> <p>" Class - AA " min.</p> <p>-----</p> <p>-----</p> <p>-----</p>	<p>Passed the test</p> <p>Passed the test</p> <p>Passed the test</p> <p>Conformed to "Class-AA"</p>



SIMOLATM
VITRIFIED TILES

S. NO.	Test Conducted	Test Results	Test Method
12	<p>Skid Resistance / Surface Slip Resistance</p> <p>(a) Condition of Test Surface : Tile Surface was cleaned thoroughly be wet cloth followed by dry cloth and ensured that the surface is completely clean and dry the time of testing.</p> <p>b) Direction of Test</p> <p>1) Parallel to sides (4 Measurements)</p> <p>2) Diagonal to sides (4 Measurements)</p>	<p>Coefficient of friction μ</p> <p>1) 0.83 2) 0.78 3) 0.77 4) 0.79</p> <p>5) 0.76 6) 0.75 7) 0.76 8) 0.76</p>	<p>As per ISO 10545 Part - 17</p>

S. NO.	Test Conducted	Test Results	Remarks
13	Moisture expansion in (mm / mtr.)	0.00	Passed the test

S. NO.	Test Conducted & Standards	Test Results	Remarks
14	Skid Resistance/ Surface Slip Resistance BS EN Standard specification EN:14411 :2016 (Group Bla)	R-11	R-11

Simola Tiles LLP



Mr. Rajesh Desai (General Manager-Marketing)